

Product Description

Bondchem WT11 is a medium strength threadlocker, that cures anaerobically to lock all types of metal threaded fasteners. WT11 is designed for applications that require future disassembly with standard hand tools, and offers excellent temperature and solvent resistance once cured. WT11 is also thixotropic, which aids assembly by reducing the migration of the liquid adhesive following application.

Typical Applications

Bondchem WT11 is well suited to a number of applications including:

- Replacing lock washers and plastic inserts.
- Locking machine tool access bolts.
- Locking and sealing gear box and drive shaft bolts.
- Securing conveyor roller bolts.
- Locking bearing cover cap screws

Instructions For Use

1. For best results clean all surfaces with a cleaning solvent and allow to dry.
2. If the metal is inactive, (see Compatibility Chart), apply suitable Bondchem primer.
3. Shake the product thoroughly before application.
4. Apply the adhesive to the fixing position of the fastener or onto the internal threads of a blind hole.
5. Use suitable methods to assemble components, and tighten to required torque level.
6. Allow to cure fully before applying load.

Properties of Uncured Material

Resin	Dimethacrylate
Colour	Light Blue
Viscosity @ 20°C	
Brookfield Sp 2 @ 20rpm	1,300-3,000 cps

Performance of Cured Material

Fixture Speed	< 20 Minutes @ 25°C
Fixture Speed with Primer	< 10 Seconds
Full Cure Time	24 hours @ 20°C
Typical Breakaway Strength	15 to 40 Nm
Typical Prevailing Strength	25 to 50 Nm
Gap Fill	0.04mm
Temperature Range	-53°C to 148°C

Packaging

Bondchem WT11 is available in 10ml, 50ml, 250ml LDPE bottles. In addition, we can offer automated dispensing lines for the bulk dispensing of this material.

Storage & Shelflife

Bondchem WT11 should be stored in a cool dry area, out of direct sunlight. Stored correctly, this grade can offer a 12 month shelf life from manufacture.

Health and Safety in Use

In case of contact with the skin, wash immediately with plenty of water. For full Health and Safety information please consult the MSDS.